



210667: Prøve 1, vanlig prosedyrer




210668: Prøve 2 vanlig prosedyre

Quartz	9.13 %
Calcite	2.37 %
Diopside	2.70 %
Chlorite Ilb	34.21 %
Magnetite	0.75 %
Talc	12.54 %
Lizardite 1T	38.12 %
Li-Montmorillonite	0.18 %




210669: Prøve 3, vanlig prosedyre

Quartz	2.61 %
Calcite	7.04 %
Diopside	15.56 %
Chlorite IIb	25.36 %
Magnetite	0.53 %
Talc	2.33 %
Lizardite 1T	11.62 %
Li-Montmorillonite	1.20 %
Albite	24.73 %
Pyrrhotite 3T	0.21 %
Titanite	8.80 %




210670: Prøve 4 vanlig prosedyre

Quartz	16.29 %
Calcite	28.93 %
Albite	18.58 %
Muscovite 2M1	18.31 %
Pyrrhotite 3T	0.05 %
Diopside	3.98 %
Chlorite 1lb	8.44 %
Kaolinite (BISH)	3.68 %
Spessartine	0.79 %
Antigorite	0.11 %
Lizardite 1T	0.03 %
Montmorillonite	0.52 %
Pyrite	0.29 %




210671: Prøve 5, vanlig prosedyre



210672: Prøve 6, vanlig prosedyre

Quartz	35.13 %
Calcite	1.09 %
Pyrite	0.02 %
Albite	17.55 %
Muscovite 2M1	33.06 %
Pyrrhotite 3T	0.81 %
Chlorite Ilb	6.95 %
Titanite	4.79 %
Spessartine	0.55 %
Lizardite 1T	0.05 %



210673: Prøve 7, vanlig prosedyre

