Contents lists available at ScienceDirect

Data in Brief

journal homepage: www.elsevier.com/locate/dib

ELSEVIER

Data Article

# Dataset regarding calcium bentonite and sodium bentonite as stabilizers for roads unbound<sup>3</sup>



# Diego Maria Barbieri<sup>a,\*</sup>, Baowen Lou<sup>a,b</sup>, Robert Jason Dyke<sup>c</sup>, Hao Chen<sup>a</sup>, Pengxiang Zhao<sup>d</sup>, Shazim Ali Memon<sup>e</sup>, Inge Hoff<sup>a</sup>

<sup>a</sup> Norwegian University of Science and Technology, Department of Civil and Environmental Engineering, Høgskoleringen 7A, Trondheim, 7491, Trøndelag, Norway

<sup>b</sup> Chang'an University, School of Highway, Nan Er Huan Road (Mid-section), Xi'an, 710064, Shaanxi, China

<sup>c</sup> Oslo Metropolitan University, Department of Civil Engineering and Energy Technology, Pilestredet 35, Oslo 0166 Norway

<sup>d</sup> Xi'an University of Science and Technology, College of Safety Science and Engineering, Yanta Road 58, Xi'an, 710054, Shaanxi, China

<sup>e</sup> Nazarbayev University, School of Engineering and Digital Sciences, Civil and Environmental Engineering, Kabanbay Batyr Ave 53, Nur-Sultan, 010000, Republic of Kazakhstan

#### ARTICLE INFO

Article history: Received 3 January 2022 Revised 25 January 2022 Accepted 27 January 2022 Available online 2 February 2022

Keywords: Calcium bentonite Sodium bentonite Road stabilisation Unbound granular materials Repeated load triaxial test

# ABSTRACT

The collected dataset derives from the laboratory testing of bentonite clay investigated as a stabilization technology for the unbound layers of road pavements. The effect of two kinds of bentonite (calcium based and sodium based) are assessed on two aggregate types commonly used as road construction materials. The investigation program, performed by means of repeated load triaxial tests, encompasses the different combinations of bentonite and aggregate types; two replicate specimens are tested dried for each condition. Considering the global need for ensuring well-performing road infrastructures while employing environmentally sound construction technologies, this dataset documenting the

\* Co-submitted with: Calcium Bentonite and Sodium Bentonite as Stabilizers for Roads Unbound, Cleaner Engineering and Technology

DOI of original article: 10.1016/j.clet.2021.100372

E-mail address: diego.barbieri@ntnu.no (D.M. Barbieri).

#### https://doi.org/10.1016/j.dib.2022.107898

2352-3409/© 2022 The Author(s). Published by Elsevier Inc. This is an open access article under the CC BY license (http://creativecommons.org/licenses/by/4.0/)

<sup>\*</sup> Corresponding author Diego Maria Barbieri Norwegian University of Science and Technology, Department of Civil and Environmental Engineering, Høgskoleringen 7A, Trondheim, 7491, Trøndelag, Norway

potential of bentonite clays used as road stabilizers can be of interest for several road stakeholders.

> © 2022 The Author(s). Published by Elsevier Inc. This is an open access article under the CC BY license (http://creativecommons.org/licenses/by/4.0/)

# Specification Table

Subject	Civil and Structural Engineering	
Specific subject area	Calcium bentonite, Sodium bentonite, Road stabilisation, Unbound granular	
	materials, Repeated load triaxial test	
Type of data	Table	
••	Image	
How data were acquired	The dataset was formed by performing Repeated Load Triaxial Test (RLTT) in	
	the laboratory.	
Data format	Raw	
Description of data collection	Repeated Load Triaxial Tests (RLTTs) were performed according to the standard EN 13286–7. A total of 12 samples was tested considering two types of bentonite (calcium based and sodium based) as stabilizing technologies and two types of aggregates (crushed rocks and natural gravel) as construction materials to be stabilized. 2 replicate samples were tested dried ( $w = 0$ %) for each combination. The deformations of the tested samples were assessed using	
	six Linear Variable Differential Transducers (LVDTs).	
Data source location	The testing campaign took place at the Department of Civil and Environmental Engineering, Norwegian University of Science and Technology (NTNU), Høgskoleringen 7A, Trondheim 7491, Norway.	
	Aggregates came from local quarries in frondelag region, Norway. Bentonite	
Data associbility	Clays were provided by industrial suppliers (see Acknowledgments section).	
Data accessibility	Republicity fidilite.	
	Calcium Denionne and sourium Denionne as stabilizers for Todus unbound	
	Data identification number (permanent identifier Dor number).	
	DUI. 10.1/052/9KWJIXgVIIIy.1	
	bttps://data.mandalay.com/datasets/0/nu/invg/mu/1	
Polated research article	D M Parbiari B Lou B L Duka H Chan D Zhao S A Mamon I Hoff	
	D. IVI. DAIDICH, D. LOU, K. J. DYKE, A. CHEH, F. ZHAO, S. A. IVIEHOH, I. HOH. Calcium Reptonite and Sodium Reptonite as Stabilizers for Peads Unbound	
	Volume 6. February 2022. Cleaner Engineering and Technology	
	https://doi.org/10.1016/j.clet.2021.100372	
	https://doi.org/10.1010/J.det.2021.100372	

# Value of the Data

- In light of the significant global need for efficient and sustainable construction and maintenance of road pavement infrastructures, the dataset is useful to appraise the stabilization potential of two types of bentonite clay (calcium based and sodium based).
- As road pavements are an important infrastructural asset for each nation's economy, the employment of green efficient technologies for road stabilization is relevant for several stakeholders such as researchers, engineers, professionals, entrepreneurs and agencies.
- The dataset can be used to quantify the stabilization potential attained by bentonite clay in roads unbound. The experimental data can be analysed according to several models to appraise resilient modulus and deformation properties.
- The rock aggregates tested in the investigation campaign have been selected as they are largely used in the central part of Norway as road construction materials.

#### 1. Data Description

The dataset is collected during an experimental testing campaign assessing the stabilization potential of bentonite clay for roads unbound [1]. Considering the huge extent of the global road network and the associated need for efficient and sustainable construction and maintenance operations [2,3], several technologies can be used to improve the mechanical properties of road unbound layers [4–6]. Being the application of bentonite an environmentally sound solution for civil construction purposes [7,8], two types of bentonite clays are considered, namely Calcium based Bentonite (CaB) and Sodium based Bentonite (NaB). They are applied on two different kinds of aggregates commonly used for road construction, namely Crushed Rock Aggregates (RCA) and Natural Gravel Aggregates (NGA). The aggregates are tested both treated with bentonite clays and untreated (Unbound Granular Material, UGM). The investigation programme is undertaken by means of Repeated Load Triaxial Test (RLTT). The formed dataset is composed by raw data and pictures of the specimens (https://data.mendeley.com/datasets/9kwjrxgvmy/1).

The experimental RLTT data contained in the folder "Data of Repeated Load Triaxial Test" are arranged in 6 subfolders as reported in Table 1. Two replicate samples (denominated "01" and "02") are tested dried for each combination and the information available for each specimen are one spreadsheet with raw data (.xlsx) and two pictures (.jpg). The amount of dry bentonite present in each sample is 0.4% in mass and it is applied at the Optimum Moisture Content (OMC) of the chosen particle size distribution w = 5% [9].

The content of all the spreadsheets is arranged according to a consistent logic [10]. The five worksheets contained in each spreadsheet are denominated "Sequence 1", "Sequence 2", "Sequence 3", "Sequence 4", "Sequence 5", which correspond to as many loading sequences forming one RLTT. Column A reports the number of the loading steps (each sequence comprises up to six steps), while column B, C, D and E display information about time *t*, temperature *T*, deviatoric pulse number and frequency *f*, respectively. The dynamic part ( $\sigma_{d,dyn}$ ) and the static part ( $\sigma_{d,st}$ ) of the deviatoric stress  $\sigma_d$  are reported in columns F and G, while, similarly, the dynamic part ( $\sigma_{t,dyn}$ ) and the static part ( $\sigma_{t,st}$ ) of the triaxial stress  $\sigma_t$  are specified in columns H and I. Six Linear Variable Displacement Transformers (LVDTs) measure the specimen deformation considering the axial elastic components ( $\varepsilon_{a,el,01}$ ,  $\varepsilon_{a,el,02}$ ,  $\varepsilon_{a,el,03}$  listed in columns F, R, T) and radial plastic components ( $\varepsilon_{r,pl,01}$ ,  $\varepsilon_{r,pl,02}$ ,  $\varepsilon_{r,pl,03}$  listed in columns Q, S, U).

The main mechanical properties that are directly relevant to road pavement engineering and can be assessed by means of RLTTs are elastic stiffness (resilient modulus,  $M_R$ ) and the resistance against permanent. As an example, considering crushed rock aggregates stabilized with calcium based bentonite, Figs. 1 and 2 depict the experimental values of  $M_R$  and axial plastic deformation, respectively, as a function of the number of load cycles N. Furthermore the trend of the experimental data can be determined considering the several regression models available in literature [11–16].

 Table 1

 Subfolders names and corresponding RLTT investigated combinations.

Numbering	Subfolder name	Aggregate type	Bentonite type
01	CRA-UGM	crushed rock	-
02	CRA-CaB	crushed rock	calcium based
03	CRA-NaB	crushed rock	sodium based
04	NGA-UGM	natural gravel	-
05	NGA -CaB	natural gravel	calcium based
06	NGA -NaB	natural gravel	sodium based



Fig. 1. Resilient modulus M<sub>R</sub> of "CRA-CaB" replicate specimens: sample 01 (a) and sample 02 (b).



Fig. 2. Axial plastic deformation of "CRA-CaB" replicate specimens: sample 01 (a) and sample 02 (b).



Fig. 3. Values of triaxial stress  $\sigma_t$  and deviatoric stress  $\sigma_d$  defining the MS LSL RLTT.

#### 2. Experimental Design, Materials and Methods

Both the crushed rock and natural gravel aggregates were derived from local quarries in Trøndelag region, Norway. They have been selected as they are largely used as construction materials in both unbound and bound layers of road pavements realized in the central part of the country [17]. The two types of calcium based and sodium based bentonite clays were supplied by industrial producers. The overarching goal of the research was to investigate environmentally friendly technologies that can be used for the construction or stabilization of road unbound layers [18,19]; in this regard, the application of bentonite is still relatively unexplored [20–22].

The research activities were accomplished performing RLTTs according to Multi-Stage Low Stress Level (MS LSL) indicated in the CEN standard "13286–7 Cyclic load triaxial test for unbound mixtures" [23]. A RLTT comprised thirty loading steps, where each of them referred to a precise combination of deviatoric stress  $\sigma_d$  and triaxial stress  $\sigma_t$  as illustrated in Fig. 3: the former one was applied according to a sinusoidal pattern using a hydraulic jack, while the latter one was applied by pressurized water. Given a constant value of  $\sigma_t$  and a dynamic deviatoric stress  $\Delta \sigma_{d,dyn}$ , the resilient modulus  $M_R$  is defined as

$$M_R = \frac{\Delta \sigma_{d,dyn}}{\varepsilon_{a,el}},\tag{1}$$

with  $\varepsilon_{a,el}$  the average axial resilient strain evaluated by the three axial LVDTs.

#### **Declaration of Competing Interest**

This work was supported by Norwegian Public Roads Administration (VegDim project, grant number 605377) and by Research Council of Norway (HERMES project, grant number 299538).

#### **CRediT Author Statement**

**Diego Maria Barbieri:** Conceptualization, Methodology, Software, Validation, Formal analysis, Investigation, Resources, Data curation, Writing – original draft, Visualization, Project administration; **Baowen Lou:** Conceptualization, Methodology, Software, Validation, Formal analysis, Investigation, Resources, Data curation, Writing – original draft; **Robert Jason Dyke:** Conceptualization, Methodology, Formal analysis, Investigation, Resources, Data curation, Writing – review & editing; **Hao Chen:** Investigation, Resources, Writing – review & editing, Visualization; **Pengxiang Zhao:** Writing – review & editing, Visualization; **Shazim Ali Memon:** Writing – review & editing, Visualization, Supervision; **Inge Hoff:** Conceptualization, Methodology, Writing – review & editing, Visualization, Supervision, Project administration, Funding acquisition.

#### Acknowledgments

This work was supported by Norwegian Public Roads Administration (VegDim project, grant number 605377) and by Research Council of Norway (HERMES project, grant number 299538). The support kindly provided by the laboratory assistants Bent Lervik, Jan Erik Molde, Lisbeth Johansen, Frank Stæhli, Tage Westrum, Torill Sørløkk, Jon Runar Drotninghaug and Laurentius Tijhuis is greatly acknowledged. Crushed rock aggregates kindly provided by Franzefoss Pukkverk avd. Vassfjell, Heimdal, Norway. Natural gravel aggregates kindly provided by Forset Grus, Tanem, Norway. Calcium bentonite kindly provided by Dantonit, Odense, Denmark. Sodium bentonite kindly provided by Imerys Metalcasting, Mannheim, Germany. The above information regarding the bentonite trade names and their suppliers are reported for informational purposes. The findings and opinions reported are those of the authors and not necessarily those of the suppliers.

#### Supplementary Materials

Supplementary material associated with this article can be found in the online version at doi:10.1016/j.dib.2022.107898.

#### References

- D.M. Barbieri, B. Lou, R.J. Dyke, H. Chen, P. Zhao, S.A. Memon, I. Hoff, Calcium bentonite and sodium bentonite as stabilizers for roads unbound, Clean. Eng. Technol. 6 (2022) 100372, doi:10.1016/j.clet.2021.100372.
- [2] A. Faiz, The promise of rural roads: review of the role of low-volume roads in rural connectivity, poverty reduction, crisis management, and livability, 2012. doi:10.17226/22711.
- [3] J.R. Meijer, M.A.J. Huijbregts, K.C.G.J. Schotten, A.M. Schipper, Global patterns of current and future road infrastructure, Environ. Res. Lett. 13 (2018), doi:10.1088/1748-9326/aabd42.
- [4] G.B. Lunsford, J.P. Mahoney, Dust Control On Low Volume roads. A review of Techniques and Chemicals Used, transs, Seattle, 2001.
- [5] D. White, P. Vennapusa, Low-cost Rural Surface Alternatives Literature Review and Recommendations, 2013 Ames.
- [6] D. Jones, A. Kociolek, R. Surdahl, P. Bolander, B. Drewes, M. Duran, L. Fay, G. Huntington, D. James, C. Milne, M. Nahra, A. Scott, B. Vitale, B. Williams, Unpaved Dust Road management. A successful Practitioner 's handbook, 2013 Denver.
- [7] C. Spaulding, F. Masse, J. LaBrozzi, Ground improvement technologies for a sustainable world, Civ. Eng. Mag. 78 (2008) 54–59, doi:10.1061/ciegag.0000168.
- [8] U. Javed, R.A. Khushnood, S.A. Memon, F.E. Jalal, M.S. Zafar, Sustainable incorporation of lime-bentonite clay composite for production of ecofriendly bricks, J. Clean. Prod. 263 (2020) 121469, doi:10.1016/j.jclepro.2020.121469.
- [9] CEN, ISO 13286-4 Test methods For Laboratory Reference Density and Water Content Vibrating hammer, 2003 Belgium.
- [10] D.M. Barbieri, J.-G. Dorval, B. Lou, H. Chen, B. Shu, F. Wang, I. Hoff, Dataset regarding the mechanical characterization of sedimentary rocks derived from svalbard for possible use in local road constructions, Data Br 34 (2021) 106735, doi:10.1016/j.dib.2021.106735.
- [11] F. Lekarp, U. Isacsson, A. Dawson, State of the art. I: resilient response of unbound aggregates, J. Transp. Eng. 126 (2000) 66–75, doi:10.1061/(ASCE)0733-947X(2000)126:1(66).

- [12] F. Lekarp, U. Isacsson, A. Dawson, State of the art. II: permanent strain response of unbound aggregates, J. Transp. Eng. 126 (2000) 76–83, doi:10.1061/(ASCE)0733-947X(2000)126:1(76).
- [13] D.M. Barbieri, I. Hoff, S. Adomako, C. Hu, Organosilane and lignosulfonate: road subsurface layers stabilisers, Adv. Mater. Pavement Perform. Predict. II. (2020) 7–11, doi:10.1201/9781003027362-2.
- [14] D.M. Barbieri, I. Hoff, C.-.H. Ho, Crushed rocks stabilized with organosilane and lignosulfonate in pavement unbound layers: repeated load triaxial tests, Front. Struct. Civ. Eng. (2021), doi:10.1007/s11709-021-0700-5.
- [15] D.M. Barbieri, I. Hoff, M.B.E. Mørk, Organosilane and lignosulfonate as innovative stabilization techniques for crushed rocks used in road unbound layers, Transp. Geotech. (2020) 22, doi:10.1016/j.trgeo.2019.100308.
- [16] D.M. Barbieri, M. Tangerås, E. Kassa, I. Hoff, Z. Liu, F. Wang, Railway ballast stabilising agents: comparison of mechanical properties, Constr. Build. Mater. 252 (2020), doi:10.1016/j.conbuildmat.2020.119041.
- [17] G. Petkovic, C.J. Engelsen, A.O. Håøya, G. Breedveld, Environmental impact from the use of recycled materials in road construction: method for decision-making in Norway, Resour. Conserv. Recycl. 42 (2004) 249–264, doi:10. 1016/j.resconrec.2004.04.004.
- [18] D.M. Barbieri, I. Hoff, H. Mork, Laboratory investigation on unbound materials used in a highway with premature damage, 10th Int. Conf. Bear. Capacit. Roads, Railw. Airfields, 2017.
- [19] D.M. Barbieri, I. Hoff, M.B.E. Mørk, Mechanical assessment of crushed rocks derived from tunnelling operations, in: W.-C. Cheng, J. Yang, J. Wang (Eds.), 5th GeoChina Int. Conf. 2018, Springer, 2019, pp. 225–241, doi:10.1007/ 978-3-319-95783-8\_19.
- [20] S. Barati, P. Tabatabaie Shourijeh, N. Samani, S. Asadi, Stabilization of iron ore tailings with cement and bentonite: a case study on Golgohar mine, Bull. Eng. Geol. Environ. 79 (2020) 4151–4166, doi:10.1007/s10064-020-01843-6.
- [21] K.L. Bergeson, S.G. Brocka, Bentonite treatment for fugitive dust control, in: Sixth Int. Conf. Low-Volume Roads, Minneapolis, 1995, pp. 261–271.
- [22] C. Li, J.C. Ashlock, D.J. White, P.K.R. Vennapusa, Mechanistic-based comparisons of stabilised base and granular surface layers of low-volume roads, Int. J. Pavement Eng. 20 (2019) 112–124, doi:10.1080/10298436.2017.1321417.
- [23] CEN, ISO 13286-7 Cyclic load Triaxial Test For Unbound Mixtures, Belgium, 2004.